

S-070 SOMAFIX THREADLOCKER HIGH

Technical Data Sheet

Issue date: 18/04/2023 Version: 0.0 TDS No.: TDS.23.103

1. Product Description

Product description Anaerobic adhesive and sealants are advanced materials with single component and solvent free feature. The products are specifically formulated for sealing, retaining, locking and bonding

of metal or metal plated assemblies. Anaerobic adhesives are stable when in contact with oxygen in air. As the product is placed between two mating metallic surfaces, where oxygen contact is vanished, polymerization starts and forms strong, vibration and pressure proof

polymer layer.

Product form Mixture

: THREADLOCKER HIGH STRENGTH Product name

Use of the substance/mixture : Anaerobic adhesive (glue)

Recommended use Industrial use Consumer use

Professional uses

2. Characteristics

Characteristics : S-070 is a single component, high strength (permanent) anaerobic threadlocker. S-070 cures when confined in the absence of air between close-fitting metal surfaces. Formulated to lock metal fasteners and thus prevent vibration loosening and leakage through the threads. S-070 is

particularly suitable for larger threaded fasteners, e.g. studs and all applications where maximum strength is needed. S-070 prevents corrosion of assembled parts.

3. Application

No information available

4. Application Instructions

- Clean male and female threads before assembly with an absorbent tissue paper to remove any cutting oil.
- The application surface should be dry and cleaned from dirt, dust and oil.
- Apply the adhesive with a 360 turn to leading threads of the male and female fittings.
- Use an absorbent tissue paper to wipe off excess jointing compound in the direction of the thread.
- Assembly parts and hold on for 24 hours at 22-24°C to ensure full curing of jointing compound.
- For disassembly, use hand tools to remove mating parts. When it is hard to dissemble at room temperature, apply local heat until reaching 250°C and disassemble while hot. Then, remove any residual cured adhesive mechanically and clean parts with a proper solvent, acetone.
- For further information, consult Safety Data Sheet and Technical Data Sheet.

5. Technical Specifications (@ 23 °C 50% RH)

Physical state : Liquid

Chemical Basis : Methacrylate ester.

: Liquid. Appearance Colour : Green

Odour : characteristic

Strength : High

: 3000 - 4000 cPs Viscosity

: > 93 °C Flash point Specific Gravity 1.04

Gap filling : Up to 0.15mm Corrosivity : Non-corrosive -50°C to 150°C Temperature Range



S-070 SOMAFIX THREADLOCKER HIGH STRENGTH

Technical Data Sheet

Issue date: 18/04/2023 Version: 0.0 TDS No.: TDS.23.103

Handlin	Handling Time		
Material of Specimen	Duration		
Brass	<60 secs		
Steel	5 to 7 mins		
Stainless Steel	6 to 8 mins		
Zinc Plated Steel	5 to 10 mins		
Aluminium	20 to 35 mins		

^{*}Average functional curing time: 1 to 3 hours

*Average full curing time: 8 to 12 hours

Unseated	Unseated assembly cured for 24 hours	
Type of Specimen	Breakaway Torque (<i>T</i> BA)	Prevailing Torque (<i>T_P</i>)
Zinc plated, M10	30 N.m	35 N.m
Stainless Steel, M10	18 N.m	20 N.m

Unseate	Unseated assembly cured for 1 week		
Type of Specimen	Breakaway Torque (<i>T</i> BA)	Prevailing Torque (<i>T_P</i>)	
Zinc plated, M10	33 N.m	39 N.m	
Stainless Steel, M10	18 N.m	20 N.m	

6. Packaging

Packaging : Aerosol

Tube 50 ml	Package 120 pcs/ctn
Tube 250 ml	Package 36 pcs/ctn

7. Shelf Life and Storage

Storage conditions : Store locked up. Store in a well-ventilated place. Keep container tightly closed. Keep cool.

Tube 50 ml	36 months (after production date, if stored at room remperature)
Tube 250 ml	36 months (after production date, if stored at room remperature)

8. Health and Safety

Adverse physicochemical, human health and environmental effects

- : May cause respiratory irritation. May cause an allergic skin reaction. Causes serious eye irritation.
- First-aid measures general : Call a poison center or a doctor if you feel unwell.
- First-aid measures after inhalation : Remove person to fresh air and keep comfortable for breathing. Call a poison center or a doctor if you feel unwell.
 - : Wash skin with plenty of water. Take off contaminated clothing. If skin irritation or rash occurs: Get medical advice/attention.

First-aid measures after skin contact



S-070 SOMAFIX THREADLOCKER HIGH STRENGTH

Technical Data Sheet

Issue date: 18/04/2023 Version: 0.0 TDS No.: TDS.23.103

First-aid measures after eye contact : Rinse cautiously with water for several minutes. Remove contact lenses, if present and easy to

do. Continue rinsing. If eye irritation persists: Get medical advice/attention.

First-aid measures after ingestion : Call a poison center or a doctor if you feel unwell.

Symptoms/effects after inhalation : May cause respiratory irritation.

Symptoms/effects after skin contact : May cause an allergic skin reaction.

Symptoms/effects after eye contact : Eye irritation.

Other medical advice or treatment : Treat symptomatically.

Hand protection : Protective gloves
Eye protection : Safety glasses

Skin and body protection : Wear suitable protective clothing

Respiratory protection : In case of insufficient ventilation, wear suitable respiratory equipment

9. Remarks

Remarks : For further information, please refer to the Safety Data Sheet

10. Standards and Certificates

No information available

Technical Data Sheet

DISCLAIMER OF LIABILITY The information in this SDS was obtained from sources which we believe are reliable. However, the information is provided without any warranty, express or implied, regarding its correctness. The conditions or methods of handling, storage, use or disposal of the product are beyond our control and may be beyond our knowledge. For this and other reasons, we do not assume responsibility and expressly disclaim liability for loss, damage or expense arising out of or in any way connected with the handling, storage, use or disposal of the product. This SDS was prepared and is to be used only for this product. If the product is used as a component in another product, this SDS information may not be applicable