

# **SOMAFIX ACRYLIC SEALANT**

# **Technical Data Sheet**

Issue date: 09/03/2017 Revision date: 01/08/2022 Version: 0.2 TDS No.: TDS.09.33

### 1. Product Description

Product description : SOMAFIX ACRYLIC SEALANT (MASTIC) is one part, elastic, acrylic based sealant which

protects against dust and water.

Product form : Mixture

Trade name : SOMAFIX ACRYLIC SEALANT

Use of the substance/mixture : Adhesives, sealants

: Industrial use Professional uses

Consumer use

Type of product : Adhesives, sealants

### 2. Characteristics

Recommended use

Characteristics : Easy application

Over-paintable

Can be easily smoothed and levelled out

Forms permanently water repellent layer after curing

Keeps flexibility quite a while after curing Good weathering and water resistance

### 3. Application

Using for repairing small cracks and grouting

· Using for PVC, aluminium, washbasin, bathtubs, closets, tiles, ceramic joints, wooden panels installation connections

Sound, water and dust insulation of vehicles

# 4. Application Instructions

- Application temperature is between +5 °C to +40 °C.
- Make sure the surface to be applied is dry and clean, free of dust and grease
- Stick both sides of surface with tapes
- Cut the cartridge/sausage tip and place it in the gun
- · Cut the cannula tip and insert into the cartridge
- Apply the sealant
- Smooth mastic with water after application and remove tapes
- Protect against water for 24 hours after application
- · Gains normal hardness within 2 weeks
- Joint width and depth ratio should be about 2:1

## 5. Technical Specifications (@ 23 °C 50% RH)

Physical state : Solid
Appearance : Paste.
Colour : white

Odour : characteristic

Curing System : Acrylic dispersion

Skin Forming Time : 15-60 minutes

Curing Rate : 1-2 mm/day

Ultimate Elongation (DIN 53504) : > 100 %

Elastic Modules at 100% (DIN 53504) :  $\ge 0.2$  mPa



# **SOMAFIX ACRYLIC SEALANT**

# **Technical Data Sheet**

Issue date: 09/03/2017 Revision date: 01/08/2022 Version: 0.2 TDS No.: TDS.09.33

Max. Tensile Strength (DIN 53504) :  $\geq$  0.3 mPa Tensile Strength (DIN 53504) :  $\geq$  0.1 N/mm<sup>2</sup>

Density : 1.66 g/cm³ ±0,01 @23°C

pH : 7.5 - 9Volume Shrinkage : 29 %Weight Loss : 18 %

Viscosity, kinematic : Not applicable Flash point : Not applicable Application Temperature :  $5 \rightarrow 40 \, ^{\circ}\text{C}$ 

### 6. Packaging

Colour : white. Black. brown. Grey.

Cartridge 310 ml	Package 24 pcs/ctn
Sausage 600 ml	Package 20 pcs/ctn

## 7. Shelf Life and Storage

Storage conditions : Store in a well-ventilated place. Keep cool.

Storage temperature :  $5 \rightarrow 35$  °C

Cartridge 310 ml	15 months (after production date if stored at room temperature)
Sausage 600 ml	15 months (after production date if stored at room temperature)

## 8. Health and Safety

First-aid measures after inhalation

Adverse physicochemical, human health and

environmental effects

: To our knowledge, this product does not present any particular risk, provided it is handled in

accordance with good occupational hygiene and safety practice : Remove person to fresh air and keep comfortable for breathing.

First-aid measures after skin contact : Wash skin with plenty of water.

First-aid measures after eye contact : Rinse eyes with water as a precaution.

First-aid measures after ingestion : Call a poison center or a doctor if you feel unwell.

Other medical advice or treatment : Treat symptomatically.

Hand protection : Protective gloves

Eye protection : Safety glasses

Skin and body protection : Wear suitable protective clothing

Respiratory protection : In case of insufficient ventilation, wear suitable respiratory equipment

## 9. Remarks

Remarks : For further information, please refer to the Safety Data Sheet

# 10. Standards and Certificates

Standards and Certificates : EN 15651-1

### Technical Data Sheet

DISCLAIMER OF LIABILITY The information in this SDS was obtained from sources which we believe are reliable. However, the information is provided without any warranty, express or implied, regarding its correctness. The conditions or methods of handling, storage, use or disposal of the product are beyond our control and may be beyond our knowledge. For this and other reasons, we do not assume responsibility and expressly disclaim liability for loss, damage or expense arising out of or in any way connected with the handling, storage, use or disposal of the product. This SDS was prepared and is to be used only for this product. If the product is used as a component in another product, this SDS information may not be applicable